

BLUESIL SP FX DEADENER 10

Description **BLUESIL SP FX DEADENER 10** is an additive for polyaddition (platinum) cured moldmaking and special effects silicone products.

Examples of applications

- Special Effects – for production of realistic “flesh-like” props for non-skin contact applications
- Shock Resistance – low loss modulus

Key benefits

- Lower durometer/hardness when added to polyaddition cured silicone products
- Higher tear strength compared to other low resilience product additives
- No post-cure is needed after initial cure is completed

Typical properties	BLUESIL SP FX DEADENER 10
Viscosity ISO 2555	2000 cP

Typical Properties of Additive Alone

Property	Value
Viscosity, 25°C (77°F), cps	2200
Specific gravity	0.97
Appearance	Colorless to light straw

When 50 parts of BLUESILSP FX DEADENER 10 are added to 50 parts of BLUESIL RTV 3611 QC A/B

Property	Value
Durometer, Shore A	9
Pot Life, min	30

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

Instruction of use Please consult your local ELKEM SILICONES sales office.

Regulation Please consult your local ELKEM SILICONES sales office.

Limitations Please consult your local ELKEM SILICONES sales office.

Packaging

- BLUESIL SP FX DEADENER 10 is available in
 - Pail of 18 KG (39.69 LB)
 - Drum of 200 KG (441 LB)

Storage and shelf life When stored in its original packaging: BLUESIL SP FX DEADENER 10 may be stored for up to 12 months from its date of manufacturing. Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.

Safety Please consult the Safety Data Sheet of: BLUESIL SP FX DEADENER 10

BLUESIL SP FX DEADENER 10

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.