

BLUESIL RTV 3625

Description **BLUESIL RTV 3625** is a low viscosity, 25 Durometer (Shore A), two component, tin catalyzed, room temperature curing silicone elastomer. It is designed as a high strength elastomer with good cured rubber properties, long library life and accurate detail reproduction. **BLUESIL RTV 3625** can be catalyzed with **BLUESIL HI-PRO GREEN**, fast setting **BLUESIL HI-PRO BLUE**.

Examples of applications

- Casting of polyester or polyurethane resins for figurine, giftware and decorative accessories
- Architectural and furniture parts and accessories
- Statuary and collectibles

Key benefits Please consult your local ELKEM SILICONES sales office.

Typical properties

TYPICAL PROPERTIES - AS SUPPLIED	
Part A - Base Component	
Color	White
Consistency	Pourable
Viscosity, cP. (mPa.s)	40,000
Part B - Catalyst Component (Hi-Pro Green)	
Color	Lt. Green
Viscosity, cP. (mPa.s)	90

TYPICAL CATALYZED PROPERTIES	Using BLUESIL™ HI-PRO GREEN, mixed at 24°C (75°F) and 50% R.H.
Mix Ratio, A:B (Parts by weight)	10:1
Viscosity, cP. (mPa.s)	44,000
Pot Life, hours (1)	4
Demold Time, hrs at RT	16
24 Hour Thick Section	
Hardness, Shore A (2)	23

TYPICAL PROPERTIES OF CURED RUBBER		Cured 7 days at 24°C (75°F) and 50% RH	
Property	Test Method	Value	
		HI-PRO GREEN	HI-PRO BLUE
Specific Gravity		1.12	1.10
Hardness (Shore A)	ASTM D2240	25	27
Tensile Strength, psi (N/mm²)	ASTM D412	660 (4.6)	620 (4.2)
Elongation (%)	ASTM D412	390	390
Tear Resistance, ppi (N/mm)	ASTM D624, Die B	132	120 (21.1)
Linear Shrinkage (3) ,%			

BLUESIL RTV 3625

24 Hours		0.2	0.4
7 Days		0.4	0.6
Temperature Range °C (°F)		-50 to 150 (-58 to 302)	

(1) Time at which material gels (2) 0.5 in. (1.27 cm) thick cup specimen (3) 8x8x0.25 in (20.3x20.3x0.64 cm) molded sheet, cured at room temperature.

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

Instruction of use

1. Stir the base (Part A) well before use (except when machine dispensing).
2. Shake the catalyst container (Part B) well before use.
3. Weigh the desired amount of base into a clean mixing container. Tip the container and roll the base all the way around the side wall up to two inches from the top. This will prevent the catalyst from becoming absorbed into the container. It is recommended that the container be filled to not more than 1/3 the container depth to allow sufficient room for expansion during the deaeration procedure.
4. Weigh the proper amount of catalyst into the container. Mix the base and catalyst together by stirring with a stiff, flat ended metal spatula until a uniform color is obtained. Scrape the container walls and bottom well to insure a thorough mix.
5. Place the container into a vacuum chamber and evacuate the entrapped air from the mixture using a vacuum pump capable of achieving 29 inches of mercury vacuum. The mixture will rise, crest and then collapse in the container. Interruption (bumping) of the vacuum may be necessary to prevent overflowing the container. Keep the mixture under full vacuum for 2-3 minutes after the material has receded in the container.
6. Bleed air slowly into the vacuum chamber. When the chamber is at atmospheric equilibrium, remove the cover plate and take out the container.
7. Pour the deaired material slowly in a steady stream from one end of the mold box so that the material flows evenly over the pattern. This should minimize entrapment of air bubbles under the flowing material. A "print" coat may be poured first over the pattern which will also help reduce the possibility of entrapping air on the pattern and in the cured rubber. A mold release (petroleum jelly) may be applied on the pattern first to improve release.
8. Allow the rubber to cure for 16-24 hours at 75±5°F (24°C) before removing the cured rubber mold from the pattern. Heat acceleration is not recommended with this product.
9. For best results, allow the mold to air cure an additional 24 hours before using it in production. Full cure is achieved in 3-7 days.
10. For bonding to wood or metals, use **BLUESIL™ V-04** primer. Follow recommendations on the **BLUESIL™ V-04** technical data sheet for best results.

PROCESSING INFORMATION

CATALYZED PROCESSING PROPERTIES ARE AFFECTED BY TEMPERATURE AND HUMIDITY VARIATION

1. For best results, mix and cure the material at 75°F (24°C) and 50% relative humidity.

BLUESIL RTV 3625

2. Higher temperature and humidity will decrease the work life and pot life of the material. The faster cure will also affect the flow properties. Refrigeration of the base prior to use in hot environments has shown to improve the handling properties of this material.
3. Lower temperatures and humidity will increase the work life and pot life of the material. The slower cure will increase the flow time. Cure temperatures below 68°F (20°C) are not recommended and have been found to cause a reduction in final cure hardness and properties.
4. It is important that the catalyst containers are tightly closed after use. Catalyst exposed to air for extended periods of time will hydrolyze (cure). An indication of hydrolysis is a film or crust formation on the surface of the catalyst. The use of hydrolyzed catalyst is not recommended and may cause incomplete cure.

Regulation	Please consult your local ELKEM SILICONES sales office.
Limitations	Please consult your local ELKEM SILICONES sales office.
Packaging	<ul style="list-style-type: none">• BLUESIL RTV 3625 is available in<ul style="list-style-type: none">○ Drum of 200 KG (441 LB)○ Pail of 20 KG (44.1 LB)
Storage and shelf life	When stored in its original packaging: BLUESIL RTV 3625 may be stored for up to 18 months from its date of manufacturing. Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.
Safety	Please consult the Safety Data Sheet of: BLUESIL RTV 3625

Visit our website www.elkem.com/silicones/

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.